

# Evidence of Performance

Classification of thermoplastic adhesives for non-structural applications



## Test report

No. 14-004192-PR03

(PB-K15-09-en-01)

Transcription to the legal successor

**Client** Follmann GmbH & Co. KG  
Heinrich-Follmann-Str. 1  
32423 Minden  
Germany

### Basis \*)

EN 204:2001-05  
Test standards  
EN 204:2001-05  
EN 205:2003-03

\*) and corresponding national versions (e.g., DIN EN)

**Product** Wood adhesive

**Designation** Folco LIT D4 W91

**Hardener** -

**Hardener addition** -

**Special features** -

Test-report 12-003437-PR03  
(PB-K15-09-en-01)  
dated 19.09.2013

### Instructions for use

## Result

Classification of wood adhesives for non-structural applications as per EN 204:2001-05



## Durability Class D4

Durability classes	Conditioning sequences	Minimum value as per EN 204 in N/mm <sup>2</sup>	Mean adhesive strength in N/mm <sup>2</sup>
D4	1	≥ 10	11.9
D4	3	≥ 4	6.7
D4	5	≥ 4	4.3

### Validity

The data and results given refer solely to the tested and described test specimen.

### Notes on publication

The ift Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

The cover sheet can be used as an abstract

### Contents

The report contains a total of 4 pages.

ift Rosenheim

05.03.2015

Dr. Ing. Odette Moarcas  
Product Engineer  
Building Materials & Semifinished Products

Stefan Hehn, Dipl.-Ing. (FH)  
Test Engineer  
Materials Testing